

AMENDMENTS TO THE CLAIMS

Pursuant to 37 C.F.R. § 1.121 the following listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of the Claims:

1. (Currently Amended) Growth method of nitride semiconductor epitaxial layer comprising:

a first step of growing a second nitride semiconductor epitaxial layer on a first nitride semiconductor epitaxial layer at a first temperature;

a second step of growing a third nitride semiconductor epitaxial layer on the second nitride semiconductor epitaxial layer at a second temperature; and

a third step of releasing nitrogen from the second nitride semiconductor epitaxial layer by collectively increasing a temperature of the first nitride semiconductor epitaxial layer, the second nitride semiconductor epitaxial layer, and the third nitride semiconductor epitaxial layer, wherein the second nitride semiconductor epitaxial layer releases nitrogen when its temperature reaches a third temperature higher than the second temperature, ~~and~~ wherein the first nitride semiconductor epitaxial layer and the third nitride semiconductor epitaxial layer retain their respective nitrogen when the second nitride semiconductor epitaxial layer reaches the third temperature~~[[.]], wherein~~ each of the first nitride semiconductor epitaxial layer and the third nitride semiconductor epitaxial layer is made of a material whose equilibrium vapor pressure of nitrogen is lower than that of the second nitride semiconductor epitaxial layer and wherein the releasing nitrogen of the third step is made using the difference in the equilibrium vapor pressures of nitrogen at the third temperature.

2. (Cancelled)

3. (Original) The growth method of nitride semiconductor epitaxial layer of claim 1, the second nitride semiconductor epitaxial layer is converted into a metal layer in the third step.

4. (Original) The growth method of nitride semiconductor epitaxial layer of claim 1, further comprising:

a fourth step of growing a fourth nitride semiconductor epitaxial layer on the third nitride semiconductor epitaxial layer after releasing nitrogen from the second nitride semiconductor epitaxial layer.

5. (Original) The growth method of nitride semiconductor epitaxial layer of claim 1, wherein the second nitride semiconductor epitaxial layer is made of $\text{In}_x\text{Ga}_{1-x}\text{N}$ ($0.5 < x \leq 1$).

6. (Original) The growth method of nitride semiconductor epitaxial layer of claim 1, wherein the first and third nitride semiconductor epitaxial layers are made of $\text{Al}_x\text{Ga}_{1-x}\text{N}$ ($0 \leq x \leq 1$).

7. (Original) The growth method of nitride semiconductor epitaxial layer of claim 1, wherein the first temperature in the first step is in a range of 300°C to 800°C.

8. (Original) The growth method of nitride semiconductor epitaxial layer of claim 1, wherein the second temperature in the second step is in a range of 300°C to 800°C.

9. (Original) The growth method of nitride semiconductor epitaxial layer of claim 1, wherein the third nitride semiconductor epitaxial layer has a thickness in a range of 1 nm to 100nm.

10. (Original) The growth method of nitride semiconductor epitaxial layer of claim 1, wherein the third temperature in the third step is 900°C or more.

11. (Original) The growth method of nitride semiconductor epitaxial layer of claim 1, wherein the first nitride semiconductor epitaxial layer is grown on a substrate.

12. (Original) The growth method of nitride semiconductor epitaxial layer of claim 11, wherein the first nitride semiconductor epitaxial layer comprises a buffer layer grown at a relatively low temperature and an un-doped GaN layer grown on the buffer layer.

13. (Original) The growth method of nitride semiconductor epitaxial layer of claim 1, further comprising:

a step of patterning the third nitride semiconductor epitaxial layer, prior to the third step.

14. (Original) The growth method of nitride semiconductor epitaxial layer of claim 3, further comprising:

a step of separating a part including the first nitride semiconductor epitaxial layer from the other part including the third nitride semiconductor epitaxial layer.

15. (Currently Amended) Growth method of nitride semiconductor epitaxial layer comprising:

growing a buffer layer on a substrate and an un-doped GaN layer on the buffer layer;

growing an InN layer on the un-doped GaN layer;

growing a GaN layer on the InN layer;

converting the InN layer into a metal layer by collectively increasing a temperature of the buffer layer, the un-doped GaN layer, the InN layer, and the GaN layer, wherein the InN layer releases nitrogen, [[and]] wherein the un-doped GaN layer and the GaN layer retain their respective nitrogen when the InN layer converts into the metal layer, wherein the un-doped GaN layer and the GaN layer are a material whose equilibrium vapor pressure of nitrogen is lower than that of the InN layer and wherein the releasing nitrogen of the InN layer is made using the difference in the equilibrium vapor pressures of nitrogen at the temperature; and

growing $\text{Al}_x\text{In}_y\text{Ga}_{1-y}\text{N}$ ($0 \leq x \leq 1$, $0 \leq y \leq 1$) on the GaN layer.

16. (Currently Amended) Growth method of nitride semiconductor epitaxial layer comprising:

a first step of growing a first nitride semiconductor epitaxial layer containing indium at a first temperature;

a second step of growing a second nitride semiconductor epitaxial layer whose equilibrium vapor pressure of nitrogen is lower than that of the first nitride semiconductor epitaxial layer, on the first nitride semiconductor epitaxial layer at a second temperature; and

a third step of releasing nitrogen from the first nitride semiconductor epitaxial layer by collectively increasing a temperature of the first nitride semiconductor epitaxial layer[[,]] and the second nitride semiconductor epitaxial layer, ~~and third nitride semiconductor epitaxial layer~~ wherein the first nitride semiconductor epitaxial layer releases nitrogen when its temperature reaches a third temperature higher than the ~~second~~ first temperature so as to convert the first nitride semiconductor epitaxial layer into a metal layer, ~~and wherein the second nitride semiconductor epitaxial layer and the third nitride semiconductor epitaxial layer retains their respective~~ its nitrogen when the first nitride semiconductor epitaxial layer reaches the third temperature, and wherein the releasing nitrogen of the first nitride semiconductor epitaxial layer is made using the difference in the equilibrium vapor pressures of nitrogen at the third temperature.

17. (Original) The growth method of nitride semiconductor epitaxial layer of claim 16, wherein the first nitride semiconductor epitaxial layer is grown on a substrate.

18. (Original) The growth method of nitride semiconductor epitaxial layer of claim 16, wherein the first nitride semiconductor epitaxial layer is grown on a compound semiconductor epitaxial layer grown on a substrate.

19. (Original) The growth method of nitride semiconductor epitaxial layer of claim 17, the first nitride semiconductor epitaxial layer is made of $\text{In}_x\text{Ga}_{1-x}\text{N}$ ($0.5 < x \leq 1$) and the second nitride semiconductor epitaxial layer is made of GaN.